



(800) 253-6300

[sales@mulhernbelting.com](mailto:sales@mulhernbelting.com)

[www.mulhernbelting.com](http://www.mulhernbelting.com)

## 1-2002: 2 Ply OHGR

**Color:** White

**Plies:** 2

**Nom. OAG:** 0.09" +/- 0.015"

**Fabric:** Polyester

**Top Surface:** 3/64" Smooth Cover

**Top Cover Thickness:** 0.046"

**Bottom Surface:** Friction Surface

**Compound:** NBR

**Work Tension:** 70 lbs./PIW

**Elongation:** Less than 2%

**Weight:** 0.054 lbs./PIW

**Minimum Pulley:** 2"

**Backflex Min. Pulley Dia.:** 3"

**Working Temp. (F):** 0 to 250

**Max. Stocked Width:** 72"

**Attributes:** FDA Compliant, Oil Resistant,  
Sliderbed Suitable

**Top Cover Coefficient of Friction:** 1.4

**Bottom Cover Coefficient of Friction:**  
0.3

**Features:** This belt features a special fabric treatment to ensure the highest ply adhesion possible and the lowest moisture saturation. 2 Ply OHGR is one of the most popular food belts available. It is used in most all FDA, USDA and agricultural applications due to its low moisture absorption and its high resistance to oil and grease. This belt is very popular in the meat and fish industry.





# Splicing Instructions



**Part Number:** 1-2002

**Part Description:** 2 Ply OHGR



**Finger Length (A):**

**Finger Width (B):**

Imperial	Metric
12"	305 mm
7"	178 mm

## Water Cooled

## Hi-Speed

**Upper Platen Temp:**

**Bottom Platen Temp:**

**Pressure:**

**Time:**

Imperial	Metric	Imperial	Metric
100 ° F	38 ° C	120 ° F	49 ° C
200 ° F	93 ° C	210 ° F	99 ° C
500 PSI	34.5 bar	300 PSI	20.7 bar
10:00 m:s	10:00 m:s	15:00 m:s	15:00 m:s

## Press Layout

## Description

## Part # to Order

	Top Heating Platen with equalizing plate	
	Silicone Paper	1020C
	Meltable Foil (optional)	8440C
	Belt	1-2002
	Silicone Paper	1020C
	Molleton Cloth	1023
	Bottom Heating Platen with equalizing plate	

test test etst etst etwst