



(800) 253-6300

sales@mulhernbelting.com

www.mulhernbelting.com

## 5-3442: 330 3/16 x 1/16 CR-MOR

**Color:** Black

**Plies:** 5

**Nom. OAG:** 0.535" +/- 0.03"

**Fabric:** Polyester/Nylon

**Top Surface:** Smooth Cover

**Top Cover Thickness:** 0.1875"

**Bottom Surface:** Smooth Cover

**Bottom Cover Thickness:** 0.0625"

**Compound:** MOR

**Work Tension:** 330 lbs./PIW

**Elongation:** Less than 4%

**Weight:** 0.25 lbs./PIW

**Working Temp. (F):** -20 to 225

**Max. Stocked Width:** 72"

**Attributes:** Cross Rigid, Oil Resistant

**Hardness:** 65a

**Minimum Pulley Chart:**

Tension Rating	Min. Pulley Dia.
Over 80%	18"
60%-80%	16"
40%-60%	14"
Below 40%, tails, snubs	12"

**Features:** 5-3442 features the same benefits as the 330 3/16" x 1/16" MOR with additional cross rigidity due to 2 additional monofilament plies. This belt is primarily used for sidewall fabrication. Do not use this belt in a troughing application. 330 3/16" x 1/16" CR-MOR is popular as the base belt in sidewall application due to its cross rigidity.

