


(800) 253-6300 sales@mulhernbelting.com www.mulhernbelting.com

3-3613: W1200 Chevron Top

Color: White Plies: 1 Nom. OAG: 0.23" +/- 0.03" Recessed OAG: 0.14" Fabric: Interwoven Polyester Top Surface: Chevron Impression Bottom Surface: Friction Surface Compound: PVC Work Tension: 120 lbs./PIW Elongation: Less than 2% Weight: 0.075 lbs./PIW Minimum Pulley: 2" Backflex Min. Pulley Dia.: 3" Working Temp. (F): 0 to 180 Max. Stocked Width: 72" Attributes: Sliderbed Suitable, FDA Compliant Top Cover Coefficient of Friction: 1.3 Bottom Cover Coefficient of Friction: 0.8

Features: 3-3613 features the popular interwoven carcass with an 1/8" high chevron impression. Refer to the chemical resistance chart when choosing a cleaning solution. NOTE---The chevron impression must be recessed to use lacing. The OAG includes the profile. Use Recessed OAG for Lacing Recommendation. W1200 Chevron Top is popular in the agricultural and food industry for the movement of bulk materials.






Splicing Instructions

Part Number: 3-3613

Part Description: W1200 Chevron Top





| | Imperial | Metric |
|--------------------|----------|--------------|
| Finger Length (A): | 3" | 76 mm |
| Finger Width (B): | 3/4" | 19 mm |

| | Water Cooled | | Hi-Speed | |
|---------------------|------------------|------------------|------------------|------------------|
| | Imperial | Metric | Imperial | Metric |
| Upper Platen Temp: | 340 ° F | 171 ° C | 330 ° F | 166 ° C |
| Bottom Platen Temp: | 340 ° F | 171 ° C | 330 ° F | 166 ° C |
| Pressure: | 50 PSI | 3.4 bar | 36 PSI | 2.5 bar |
| Time: | 01:00 m:s | 01:00 m:s | 03:00 m:s | 03:00 m:s |

| Press Layout | Description | Part # to Order |
|--------------|--|-----------------|
| | Top Heating Platen with equalizing plate | |
| | Impression Pad | |
| | Meltable Foil (optional) | 8340C |
| | Belt | 3-3613 |
| [] | Teflon | 6-3000 |
| | Bottom Heating Platen with equalizing plate | |

For high stress applications splice with reinforcing fabric.